

**Product: 2000**



<b>Dry Adhesion (lbf)</b>	
Aluminum	21.68/65c
Brick	14.97/100a
Concrete	22.26/100c
Luan (Wood)	26.27/85c
Steel	7.58/100a
Tensile at Peak (psi)	213.4
Elongation at Break (%)	543.33
Type "A" Hardness	37
Tack Free time (ASTM method)	3 hours
Cure rate (1/4 x 1/4 bead)	1 day

Geocel, LLC  
P.O. Box 398  
Elkhart, IN 46515

Questions?  
Call Customer Service at 800-348-7615

02/09