

Product: Proflex



Dry Adhesion (lbf)	
Aluminum	16.44/100a
Concrete	21.04/100a
Copper	25.76/40c
Galvanized Steel	23.33/50c
Kynar	22.93/60c
Luan (Wood)	17.09/100a
Shingle	5.23/sf
Tile	30.02/55c
Vinyl	18.57/90c
Tensile at Peak (psi)	224.42
Elongation at Break (%)	1025.55
Type "A" Hardness	39
Tack Free time (ASTM method)	120 mins
Cure rate (1/4 x 1/4 bead)	1 day

Geocel, LLC
P.O. Box 398
Elkhart, IN 46515

Questions?
Call Customer Service at 800-348-7615

09/09