

Product: 3300



Dry Adhesion (lbf)	
Aluminum	29.51/100C
Brick	19.7/80C
Concrete	30.3/100C
Galvanized Steel	10.1/100A
Glass	18.3/40C
Kynar	10.8/100A
Luan (Wood)	25.6/100C
Steel	22.5/100C
Tile	27.5/100C
Tensile at Peak (psi)	351.98
Elongation at Break (%)	1093.3
Type "A" Hardness	37.6
Tack Free time (ASTM method)	3 hours
Cure rate (1/4 x 1/4 bead)	2 days

Geocel, LLC
P.O. Box 398
Elkhart, IN 46515

Questions?
Call Customer Service at 800-348-7615

10/10