

Product: 3500



| | |
|------------------------------|------------|
| Dry Adhesion (lbf) | |
| Aluminum | 25.01/100c |
| Brick | 25.86/75c |
| Concrete | 27.18/100c |
| Galvanized Steel | 13.15/100a |
| Glass | 14.77/55c |
| Kynar | 20.37/100c |
| Luan (Wood) | 24.86/100c |
| Steel | 22.83/100c |
| Tile | 11.1/100a |
| | |
| Tensile at Peak (psi) | 204.55 |
| Elongation at Break (%) | 827.55 |
| | |
| Type "A" Hardness | 43 |
| | |
| Tack Free time (ASTM method) | 40 mins |
| | |
| Cure rate (1/4 x 1/4 bead) | 2 days |

Geocel, LLC
P.O. Box 398
Elkhart, IN 46515

Questions?
Call Customer Service at 800-348-7615

10/09