

Product: Advanced RV



Dry Adhesion (lbf)	
Aluminum	11.71/100c
Brick	10.34/90c
Concrete	12.56/100c
EPDM (White)	5.16/20c
Galvanized Steel	10.56/100c
Glass	11.31/100c
Luan (Wood)	11.80/100c
PVC	7.77/100c
Steel	11.54/100c
Tile	11.30/100c
Vinyl	11.11/100c
Tensile at Peak (psi)	106.99
Elongation at Break (%)	428.33
Type "A" Hardness	29
Tack Free time (ASTM method)	40 mins
Cure rate (1/4 x 1/4 bead)	2 days

Geocel, LLC
P.O. Box 398
Elkhart, IN 46515

Questions?
Call Customer Service at 800-348-7615

07/09