

Product: Instant Gutter Seal



Dry Adhesion (lbf)	
Aluminum	15.99/100a
Concrete	24.25/100a
Fiber Cement	13.63/100a-sf
Fiberglass	29.04/100a - sr
Kynar	19.90/100a
Luan (Wood)	18.37/100a
Shingle	8.87/100a-sf
Steel	16.61/100a
Tensile at Peak (psi)	637.33
Elongation at Break (%)	929.17
Type "A" Hardness	42.867
Tack Free time (ASTM method)	20 mins
Cure rate by weight loss (internal)	6 days

Geocel, LLC
P.O. Box 398
Elkhart, IN 46515

Questions?
Call Customer Service at 800-348-7615

07/11