

Product: Mortar Seal



Dry Adhesion (lbf)	
Aluminum	12.3/100c
Brick	11.6/100c
Concrete	12.1/100c
Glass	11.8/95c
Luan (Wood)	12.4/100c
Steel	12.6/100c
Tile	12.0/85c
Tensile at Peak (psi)	200.2
Elongation at Break (%)	116.7
Type "A" Hardness	48
Tack Free time (ASTM method)	19 mins
Cure rate (1/4 x 1/4 bead)	2 days

Geocel, LLC
P.O. Box 398
Elkhart, IN 46515

Questions?
Call Customer Service at 800-348-7615

12/10