

Product: Proflex Multipurpose Brushable



Dry Adhesion (lbf)	
Aluminum	27.00/sr
Brick	18.76/100a
Concrete	24.10/100c
Glass	27.11/100c
Luan (Wood)	18.51/100c
Steel	27.59/100c
Tile	32.18/100c
Vinyl	27.62/100c
Tensile at Peak (psi)	301
Elongation at Break (%)	565
Type "A" Hardness	50
Tack Free time (ASTM method)	2.4 hrs
Cure rate by weight loss (internal)	5 days
VOC Content	
grams/liter (g/l)	470.01
% by weight	51.15

Geocel, LLC
P.O. Box 398
Elkhart, IN 46515

Questions?
Call Customer Service at 800-348-7615

01/10