

Product: SPEED GRIP



Dry Adhesion (lbf)	
Aluminum	18.9/100C
Brick	13.9/100C
Concrete	17.5/100C
Galvanized Steel	17.9/95C
Glass	17.4/100C
Kynar	15.0/45C
Luan (Wood)	16.4/100C
Shingle	12.0/30C
Steel	17.1/1000C
Steel (Rusted)	15.9/100C
Tile	18.5/100C
Vinyl	15.8/95C
Tensile at Peak (psi)	374
Elongation at Break (%)	126
Type "A" Hardness	74
Tack Free time (ASTM method)	10 MIN
Cure rate (1/4 x 1/4 bead)	1 DAY

Geocel, LLC
P.O. Box 398
Elkhart, IN 46515

Questions?
Call Customer Service at 800-348-7615