

**Product: Watershield Brush**



<b>Dry Adhesion (lbf)</b>	
Aluminum	17.9/100a
Brick	18.4/100a
Concrete	23.5/40c
Galvanized Steel	19.5/85c
Glass	21.5/100c
Kynar	17.5/80c
Luan (Wood)	23.6/85c
Steel	17.8/100c
Tile	24.1/100c
Vinyl	17.1/100c
Tensile at Peak (psi)	225
Elongation at Break (%)	413
Type "A" Hardness	40
Tack Free time (ASTM method)	45 min
Cure rate by weight loss (internal)	2 days

Geocel, LLC  
P.O. Box 398  
Elkhart, IN 46515

Questions?  
Call Customer Service at 800-348-7615

12/10