

Product: 1500 SL



Dry Adhesion (lbf)	
Aluminum	13.84/100c
Brick	12.71/100c
Concrete	14.72/100c
Galvanized Steel	9.44/100c
Glass	11.93/100c
Luan (Wood)	8.77/100c
Shingle	9.54/sf
Steel	13.07/100c
Tile	14.64/100c
Tensile at Peak (psi)	90.04
Elongation at Break (%)	730.83
Type "A" Hardness	31
Tack Free time (ASTM method)	120 mins
Cure rate by weight loss (internal)	4 days